

HAMMOND 100Y LITHARGE

ELECTRONIC GRADE TECHNICAL DATA

APPLICATIONS

This material is used as a source of lead in glass and polymer stabilizers where higher purity is required. It is milled to achieve a fine, narrow particle size range for enhanced reactivity and the greatest degree of consistency in solid state reactions.

PHYSICAL PROPERTIES

Color	Yellow
Form	Powder
Specific Gravity	9.5 grams
Apparent Density	26 - 32 g/in ³
Molecular Weight	223.21
Melting Point	1630°F (888°C)
Median Particle Size	3.5 - 4.5 μm
Screen Analysis	0.05% > 325 mesh
(U.S. Standard Sieve)	99.5% < 325 mesh

CHEMICAL COMPOSITION

PbO (Litharge)	99.85% minimum
Pb (Free Lead)	0.10% maximum
Pb₃O₄ (Red Lead)	0.05% maximum

TRACE ELEMENTS

Element	Maximum %
Iron Oxide	0.0025
Zinc Oxide	0.0008
Copper Oxide	0.0010
Silver	0.0015
Bismuth Oxide	0.0150
Arsenic Oxide	0.0004
Antimony Trioxide	0.0004
Tin Oxide	0.0004
Nickel	0.0002
Tellurium	0.0002
Cadmium	0.0002
Cobalt	0.0002
Chromium	0.0002
Manganese	0.0002
Selenium	0.0002

PACKAGING

50 lb. / 22.68 kg Paper bags / pails
28-gallon steel drums (600 lbs. / 272.16 kg)
Sling bags (<2,000 lbs. / 907.19 kg)
Special packaging available upon request

NOTES

This data sheet illustrates typical values for this product. If specific characteristics are required that are different from these values or if custom packaging is required, please contact your area sales representative.

HAMMOND
THE CHANGE CATALYST®

Hammond Lead Products
2901 Carlson Drive, Suite 200
Hammond, IN 46323 USA
Phone: (219) 931-9360
Fax: (219) 931-2140



HAMMONDGLOBAL.COM

©Hammond Group Inc. 2023 · Proprietary Information: Not to be disclosed to a third party without the express written consent of Hammond Group Inc.